

**Chemical Resistance of SINOYQX Melamine Foam in Different Mediums**

Classification	Medium and Concentration	Stability
Acid	HCL, 10%	-
	Phosphorous acid, 50%	-
	Sulphuric acid, 10%	-
	Nitric acid, 10%	-
	Acetic acid, 90%	+
Alkali	Ammonia water, 25%	-
	Sodium hydroxide solution, 50%	+
Alcohol	Methanol	+
	Ethanol	+
	Isopropyl alcohol	+
	Butyl alcohol	+
	Glycerol	+
Hydrocarbon	Gasoline	+
	Liquid paraffin	+
	Methylene chloride	+
	Styrene	+
Others	Distilled water	+
	Salt water 3.6%	+
	Butyl Acetate	+
Remarks: “+” means stable “-” means unstable		

Issued by SINOYQX

Version 2.23