

## SINOYQX YQX-G+ Melamine Foam Data Sheet

Items	Index
Apparent Density (kg/M <sup>3</sup> )	9(±1)
Rebounding Ratio (%)>	65
Tensile Strength (Kpa)>	120
Elongation at break (%)>	45
Compression hardness 25%>	250
Compression permanent deformation%<	13
Indentation hardness 25%>	340
Thermal conductivity (mW/mK) <	0.034
NRC	0.9
Radionuclide limit	0
Oxygen (%) >	32.3
Smoke Density <	30
Flammability	UL-V0, HF-1
Operating Temperature (°C)	-190°C~200°C
Dimension (mm)	2500*1250~1270*350 (Block) ※ 2550*1300*4200(Bun)

※ **The width with skin is 1250mm, if the Formaldehyde release is less than 0.1 ppm for acoustic application.**

Issued by SINOYQX

Version2.30

Address: Rm.2908, Unit 3, Building 3, No.388, Xishun Street, Huazhaobi, Jinniu District, Chengdu, 610000, Sichuan, China.

Tel: 0086-28-8411-1861 Fax: 0086-28-8459-0692 Web: [www.sinoyx.com](http://www.sinoyx.com) E-mail: [info@sinoyx.com](mailto:info@sinoyx.com)

SINOYQX and its logo are trademarks of SINOYQX or one of its subsidiaries.

Copyright © 2023 SINOYQX All rights reserved.